## **Aqualon® Typical Properties 2012**

Base Fabric Woven Polyester

Finished Width 60"

Finished Square Yard Weight 8.75 oz./sq. yd.

Base Fabric Count 96 x 33

Finish/Coating Face Pigmented Vinyl Resin Coated

Finish / Coating Underside Clear Water Resistant

Tongue Tear, lbs 22 X20
Tensile, lbs: ASTM 5034 450 X 350
Chatillon Hand lbf: 6.00

Height Hydrostat, cm: AATCC Method 127 90+ Spray Rating: AATC Method 22 100 Bag Test, 8 and 24 hours: GSF Method Pass

UV Resistance 5 years

Values noted herein are typical results.