

TEST METHOD	RESULT
Fabric Weight ASTM D3776	29 oz/sy
Width NTC 228	54 inches (137cm)
Bond Strength Adhesion of Vinyl Fim to Fabric Warp ASTM D751	>15 n/in (>3.4 lbf/in)
Bond Strength Adhesion of Vinyl Fim to Fabric Filling ASTM D751	>15 n/in (>3.4 lbf/in)
MD Stretch (Warp) SAE J855 (NT 8.2.4-058 Test N°1)	40% +/- 10%
AMD Stretch (Fill) SAE J855 (NT 8.2.4-058 Test N°1)	40% +/- 10%
Resistance of Synthetic Polymeric Material to Fungi ASTM G-21 (No Fungal Growth)	Pass
Antifungal Activity Assement on Textile Materials AATCC 30, Test III (No Growth)	Pass
Colorfastness SAE J 2527 @1500 kJ	4+
Crocking AATCC 8 (Wet and Dry)	5
Abrasion Resistance ASTM D4157-07	50,000 cycles
Tear Strength MD ASTM D 2261	15.8 lbs
Tear Strength CD ASTM D 2261	9.0 lbs
Cold Crack Federal Test Standard (CFFA 6 2007)	-10°F
W-Flex ASTM D2097-03	25,000 cycles
302 Burn Test MVSS302	Pass
California Technical Bulletin #117 TB 117-2013	Pass
Warranty	3 Years See website for complete details.
Warranty Microbial Pinking Resistant	N/A