

Hydrofend® Specs

Fabric Weight ASTM D3776	8oz/yard ²
Roll Size	100 yards (91 meters)
Finished Fabric Width ASTM D3774	60 inches (152cm)
Hydrostatic Test AATCC 127	200cm (79 inches)
Spray (Large) AATCC 22	100
Break Strength ASTM D5034	Warp: 375 pounds Fill: 345 pounds
Tear Strength ASTM D2261	Warp: 40 pounds Fill: 40 pounds
Circular Bend Stiffness ASTM D4032	5.09
Wyzenbeek Abrasion ASTM D4157	100,000 double rubs
Color Fastness to Light AATCC 2261	4-5 after 2,000 hours
Warranty	5 years (3 years for Deep Maroon)
Mullen Burst ASTM D3786	200+ psi
Taber Abrasion ASTM D3884-09	9,000 cycles (H-22 wheels, 1,000 gram load)
Water Vapor Transmission ASTM E96B	326 grams
Cold Crack -40°F, ASTM D1912	Pass



The ultimate defense against the weather.