



Crew protection with
high resistance to tear



Snow white 102 in

F4463-10309



White 102 in

F4463-03244



Ivory 102 in

F4463-10081

Stamoid

Open

Applications:

Crew protection: sprayhoods, bimini tops, cockpit enclosures and more

■ Protection

Stamoid® is waterproof, highly resistant to severe weather conditions, and provides total protection against UVB rays.

■ Durability


Exceptional strength, resistance to UV and mold and very easy to clean to keep your boat looking beautiful longer.

■ Tear resistance

Maximum tear resistance for heavy-duty crew-protection applications.

■ Technical properties

Standards

Coating	2 sides PVC	
	Multi-layer composite	
Base cloth	1100 dtex PES HT	TERSUISSE 
Weight	19.2 oz / sqyd	EN ISO 2286-2
Width	102 in	
Standard length	32.81 lyds	

■ Physical properties

Tensile strength (warp/weft)	517 / 517 lbs / 2in	EN ISO 1421
Tear strength (warp/weft)	67 / 56 lbs	DIN 53.363
Color light fastness	≥7 (Xenotest 750 hours)	ISO 105-B02
Extreme light stability	$\Delta E_{lab} < 3$ (UVA340/2000 hours)	QUVTEST T30-036
UV filtrations	UPF 50+	NF EN 13758-1+A1
Mold resistance	Degree 0, excellent	EN ISO 846-A
Extreme use temperatures	-4°F / +158°F	

■ Certifications, warranties, recycling



**5 year
warranty**

The technical data above are average values with a +/- 5% tolerance.

The buyer of our products is fully responsible for their application or their transformation concerning any possible third party. The buyer of our products is responsible for their implementation and installation in compliance with standards, codes of practice and safety regulations in force in destination countries.

To ensure warranty effectiveness, refer to applicable warranty certificate, available on demand.

The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subject to changes prompted by technological developments. We reserve the right to modify their characteristics at any time. The buyer of our products is responsible for checking the validity of the above data.