

# Typical Properties of Aqualon® Edge Soft

Tested Property	Aqualon Edge Soft
Width, inches: GSF Method	59
Weight, oz/yd2: ASTM D 3774	11.0
Count: ASTM D 3775 Warp x Fill	96 x 33
Chatillon Hand, lbf: ASTM D 4032	6.00
Height Hydrostat, cm: AATCC Method 127	90+
Spray Rating: AATCC Method 22	100
Bag Test, 8 & 24 hrs: GSF Method	Pass
Water Permeability After Cold Crack, cm: AATCC 169	60+ With no visual signs of cracking
Heat Buildup Test (Temperature Reduction °F) ASTM D 4803	25 °F