

CAPITANO™

TECHNICAL DATA SHEET

| TEST METHOD | RESULT |
|---|------------------------|
| Fabric Weight ASTM D3776 | 30 oz/yd. |
| Width NTC 228 | 54 inches (137cm) |
| Bond Strength Adhesion of Vinyl Fim to Fabric Warp ASTM D751 | >15 n/in (>3.4 lbf/in) |
| Bond Strength Adhesion of Vinyl Fim to Fabric Filling ASTM D751 | >15 n/in (>3.4 lbf/in) |
| Resistance of Synthetic Polymeric Material to Fungi ASTM G-21 (No Fungal Growth) | Pass |
| Antifungal Activity Assesment on Textile Materials AATCC 30, Test III (No Growth) | Pass |
| Colorfastness SAE J 2527 @1500 kj | 4+ |
| Croaking AATCC 8 (Wet and Dry) | 5 |
| Abrasion Resistance ASTM D4157-07 | 50,000 cycles |
| Tear Strength MD ASTM D 2261 | 17.6 lbs |
| Tear Strength CD ASTM D 2261 | 12.7 lbs |
| Cold Crack Federal Test Standard (CFFA 6 2007) | -10°F |
| W-Flex ASTM D2097-03 | 25,000 cycles |
| NFPA 260 Class 1 | Pass |
| UFAC Fabric Class 1 | Pass |
| BIFMA Class A | Pass |
| AB 2998 | Pass |
| California Technical Bulletin #117 TB 117-2013 | Pass |
| Warranty Loss of Strength or color due to normal usage and exposure, and resistance to mildew and atmospheric chemicals | 5 Years |