

TEST METHOD	RESULT
<b>Fabric Weight</b> ASTM D3776	29 oz/ly
<b>Width</b> NTC 228	54 inches (137cm)
<b>Bond Strength Adhesion of Vinyl Fim to Fabric Warp</b> ASTM D751	>15 n/in (>3.4 lbf/in)
<b>Bond Strength Adhesion of Vinyl Fim to Fabric Filling</b> ASTM D751	>15 n/in (>3.4 lbf/in)
<b>MD Stretch (Warp)</b> SAE J855 (NT 8.2.4-058 Test N°1)	40% +/- 10%
<b>AMD Stretch (Fill)</b> SAE J855 (NT 8.2.4-058 Test N°1)	40% +/- 10%
<b>Resistance of Synthetic Polymeric Material to Fungi</b> ASTM G-21 (No Fungal Growth)	Pass
<b>Antifungal Activity Assement on Textile Materials</b> AATCC 30, Test III (No Growth)	Pass
<b>Colorfastness</b> SAE J 2527 @1500 kj	4+
<b>Crocking</b> AATCC 8 (Wet and Dry)	5
<b>Abrasion Resistance</b> ASTM D4157-07	50,000 cycles
<b>Tear Strength MD</b> ASTM D 2261	15.8 lbs
<b>Tear Strength CD</b> ASTM D 2261	9.0 lbs
<b>Cold Crack</b> Federal Test Standard (CFFA 6 2007)	-10°F
<b>W-Flex</b> ASTM D2097-03	25,000 cycles
<b>302 Burn Test</b> MVSS302	Pass
<b>California Technical Bulletin #117</b> TB 117-2013	Pass
<b>Warranty</b>	3 Years See website for complete details.
<b>Warranty</b> Microbial Pinking Resistant	N/A