

PRODUCT PROFILE

Rev.1 11/23



Commercial Heavy 430FR is a high quality knitted flame retardant shade fabric designed for tension structures, awnings and shade sails specifically for commercial architectural applications; supplied in bulk rolls.

- Strong HDPE 100% recyclable fabric won't rot or absorb moisture.
- Stentered (heat-set) to reduce shrinkage and for ease of fabrication.
- Certified to California State Fire Marshall CSFM 1237.1 and complies with NFPA701 across all colour variants.
- 12-year UV degradation warranty on fabric.
- · 100% Lead and Phthalate free
- · Engineered in Australia to meet the harsh climate

FABRIC PROPERTIES

(AS 2001.2.13) mass per unit

Nominal fabric mass 12.7 oz./yd²; 430 gsm \pm 20; Approximate thickness 0.06in. / 1.6 mm

ROLL SPECIFICATIONS

Nominal width:

Length:

Approx. roll weight:

Approx. roll diameter:

Core diameter:

9 ft. 10 in. / 3.0m (unfolded)

131 ft. 3 in. / 40m

119 lbs / 54 kg

1 ft. / 0.30 m

3 in. / 76 mm

USAGE INSTRUCTIONS

Do not use against flames.

Contact with organic solvents, halogens or highly acidic substances may reduce the service life of the fabric and void the warranty

Biaxial elastic material properties available on request.

SUGGESTED SPECIFICATION

Shade cloth fabric shall be compliant to Australian standard AS 4174:2018 and shall be GALE Commercial Heavy 430 FR knitted with HDPE monofilament offering a UVE Protection Category of "Effective".

FLAMMABILITY

CSFM Title 19 1237.1 NFPA 701 Test Methods 1 & 2 ASTM E84 19B Class A NFP92-503 Class M1 in process

Each color individually tested and passes all certification criteria for above. Test results available upon request.

PERFORMANCE

ASTM D5034

Tensile Strength and Elongation

Maximum Force – Warp (Mean)

Elongation at Maximum Force – Warp (Mean)

Maximum Force – Weft (Mean)

Elongation at Maximum Force (Mean)

106 %

ASTM D2261

Tearing Strength - Tongue (Single Rip)

Mean Force – Warp 55.8 lbf
Mean Force – Weft 48.7 lbf

ASTM D6797

Bursting Strength – Ball Burst (Constant Rate of Extension)
Mean Force 376 lbf

(AS 4174:2018) Shade Protection Fabric Performance

Colour	Cover Factor	Shade Factor	UV-Vis Trans %	UVR Trans %	UVR Block %	UVE %	Protection Category
Aquatic Blue	86	85.7	14.3	14.1	85.9	85	Effective
Black	87	87.5	12.5	12.5	87.5	87	Effective
Bright Green	85	84.1	15.9	14.6	85.4	84	Effective
Brunswick Green	84	84.5	15.5	15.5	84.5	84	Effective
Charcoal	86	86.8	13.2	13.1	86.9	86	Effective
Deep Ochre	87	87.0	13.0	12.9	87.1	86	Effective
Desert Sand	85	79.8	20.2	14.7	85.3	84	Effective
Emerald	86	86.2	13.8	13.5	86.5	86	Effective
Natural	87	75.9	24.1	12.7	87.3	87	Effective
Navy Blue	87	87.4	12.6	12.5	87.5	87	Effective
Orange	85	75.5	24.5	14.8	85.2	84	Effective
Red	86	75.5	24.5	13.8	86.2	86	Effective
Royal Purple	87	86.8	13.2	12.5	87.5	87	Effective
Steel Grey	86	85.9	14.1	13.3	86.7	86	Effective
White	86	71.5	28.5	13.8	86.2	86	Effective
Yellow	86	74.1	25.9	13.3	86.7	86	Effective



















ANZ MIDDLE EAST AMERICAS ASIA EUROPE P 1800 331 521 P +971 4 881 7114 P 1800 560 4667 P 1800 331 521 P 1800 560 4667

www.galecommercial.com