

# TRIVANTAGE

ORDER. DONE. GOOD CALL.



**STYLE: C18403**  
**Super 18**  
**Vinyl Coated Polyester**

## TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 18 oz. / yd.<sup>2</sup>

Grab Tensile

ASTM D-751 450 x 425 lbs.

Strip Tensile

ASTM D-751 260 x 250 lbs. / in.  
Procedure B

Tongue Tear

ASTM D-751 90 x 80 lbs.  
8x10 Specimen @ 12 in. / min.

Adhesion

ASTM D-751 10 lbs. / in.  
RF Weld

Puncture Resistance

ASTM D-4833 185 lbs.

Hydrostatic Resistance

ASTM D-751 700 psi  
Procedure A

Low Temperature

ASTM D-2136 -40 ° F

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose.

There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by Trivantage, LLC.