



Typical Properties

TESTED PROPERTY	HYDROFEND® CVR
Fabric Weight ASTM D3776	7.4 oz/yard ²
Roll Size	100 yards (91 meters)
Finished Fabric Width ASTM D3774	60 inches (152cm)
Hydrostatic Test AATCC 127	39 inches (100cm)
Spray (Large) AATCC 22	100
Break Strength ASTM D5034-95	Warp: 375 pounds Fill: 315 pounds
Tear Strength ASTM D2261-96	Warp: 30 pounds Fill: 25 pounds
Abrasion ASTM D4157-13 Wirescreen	100,000 cycles
Water Vapor Transmission ASTM 96, Method B	141 g/24 hr M2
Cold Crack -40°F, FTMSM D191, Method 5874	Pass
Warranty	5 years

800.786.1876 ▪ trivantage.com



Hydrofend® and Trivantage® are registered trademarks of Glen Raven, Inc.