

TRIVANTAGE

ORDER. DONE. GOOD CALL.



Lam-A-Lite
Style# C10641
Vinyl Laminated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 10 oz. / yd.²

Grab Tensile

ASTM D-751 130 x 150 lbs.

Strip Tensile

ASTM D-751 70 x 80 lbs. / in.
Procedure B

Tongue Tear

ASTM D-751 35 x 40 lbs.
8x10 Specimen @ 12 in. / min.

Trap Tear

ASTM D-751 25 x 35 lbs.

Adhesion

ASTM D-751 20 lbs. / in.
RF Weld

Cold Crack

ASTM D-2136 -40 ° F

Flame Resistance

Cal. Fire Marshal-Title 19 Pass
NFPA 701 Pass
FAR 25.853 (a) Pass

Date Issued: September 6, 2010