

TRIVANTAGE

ORDER. DONE. GOOD CALL.



Lam-A-Lite

Vinyl Laminated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751

13 oz. / yd.²

Grab Tensile

ASTM D-751

210 x 225 lbs.

Strip Tensile

ASTM D-751

Procedure B

130 x 135 lbs. / in.

Tongue Tear

ASTM D-751

8x10 Specimen @ 12 in. / min.

40 x 50 lbs.

Trap Tear

ASTM D-751

60 x 40 lbs.

Adhesion

ASTM D-751

RF Weld

20 lbs. / in.

Cold Crack

ASTM D-2136

-40 ° F

Flame Resistance

Cal. Fire Marshal-Title 19

NFPA 701

FAR 25.853 (a)

Pass

Pass

Pass

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose.

There are no warranties, expressed or implied including any warranty of merchantability, unless specified in writing and signed by Trivantage, LLC.