



## TYPICAL PROPERTIES REPORT

PROPERTY		TEST METHOD	AVERAGE TEST RESULTS	
PHYSICAL PROPERTIES				
English	Metric		English	Metric
Weight, (oz./yd <sup>2</sup> )	g/m <sup>2</sup>	ASTM D3776	15 oz. +/- 10%	508 g +/- 10%
Adhesion. (lbs./2 in.)	N/50 mm	ASTM D751 (Free Peel)	6.5 Minimum	29 Minimum
Breaking Strength (lbs./in)	N/25 mm	ASTM D5034	W 245 F 245	W 1090 F 1090
Tear Strength (lbs.)	N	ASTM D2261	W 11 F 11	W 49 F 49
Hydrostatic Burst (PSI)	kPa	ASTM D751/A	435	2999

The information contained in this report is believed to be reliable. It is offered in good faith and intended for use as a general guide. Herculite/Strataglass makes no guarantee of results and assumes no obligation or liability whatsoever in connection with the possible use of this information. This report, including any statements concerning the possible use of our products, is not a license to operate under, or intended to suggest infringement of any existing patents.

Strataglass® is a registered trademark of Herculite Products, Inc., Emigsville, PA

### HERCULITE PRODUCTS, INC.

P.O. Box 435, Emigsville, PA 17318

(800) 772-0036 (717) 764-1192

FAX: (717) 764-5211

www.herculite.com customercare@herculite.com