



Received: 06/20/2014	Completed: 06/26/2014	Letter: J	CT	P.O.#:	Test Report #:	3-02786-0-
----------------------	-----------------------	-----------	----	--------	----------------	------------

Client's Identification	Product Identification: Tex Tex / Yuri Material Two Side Coated Vinyl on Polyester Fabric.
-------------------------	--

Tested For: Doug Johnson Graniteville Specialty Fabrics 511 Leitner Street Graniteville, SC 29829	Key Test: ASTM E 84 (BLDG) 1185 Tel: 1-(803)-663-2350 Fax: 1-(803)-663-2908	Ext:
---	---	------

BLDG (IBC): LE 2012; R 06/12; V 6/12 PC: ME /jd
ASTM E84: LE 2012; R 06/12; V 06/12

TEST PERFORMED: ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials

REFERENCE: Comparable to: UL 723 - Standard for Test for Surface Burning Characteristics of Building Materials

APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.007"

PRODUCT CATEGORY:

- ☒ Textile Type Product
☐ Vinyl Type Product
☐ Other than Textile Type or Vinyl Type Product: _____

-- See Page 3 for "DISCUSSION" pertaining to Room Corner Fire Tests. --

SPECIMEN MOUNTING:

- ☒ Self Supporting: The test specimen, the face of which was 23" \pm 1" x 24', was such that it remained in position in the tunnel during the fire test, and no additional support was required.
- ☐ Adhered to IRC: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 23" \pm 1" x 24'.
- ☐ Adhered to Gypsum: The test specimen was adhered to 5/8" thick Type X gypsum board, to form a test specimen the face of which was 23" \pm 1" x 24'.
- ☐ Unadhered: The 23" \pm 1" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.
- ☐ Other: _____

Received:06/20/2014	Completed:06/26/2014	Letter: J	CT	P.O.#:	Test Report #:	3-02786-0-
---------------------	----------------------	-----------	----	--------	----------------	------------

Client's Identification	Product Identification: Tex Tex / Yuri Material Two Side Coated Vinyl on Polyester Fabric.
--------------------------------	--

Tested For: Doug Johnson Graniteville Specialty Fabrics 511 Leitner Street Graniteville, SC 29829	Key Test: ASTM E 84 (BLDG) Tel: 1-(803)-663-2350 Fax: 1-(803)-663-2908	1185 Ext:
---	---	-------------------------

REMARKS: None.

RESULTS:

Flame Spread Index: 15
Smoke Developed: 145

CONCLUSION: Based on the above Results and Code Classification System the item tested is assigned a:

- ☒ Class I or A rating
- ☐ Class II or B rating
- ☐ Class III or C rating
- ☐ Fails to achieve a minimum classification thereby rendering the product unsuitable in terms of code requirement

DATA SUMMARY:

Time to Ignition: 00.03 minutes
Maximum Flame Spread "Distance": 03.29 feet
Maximum Flame Spread "Time": 00.40 minutes

CODE CLASSIFICATION SYSTEM:

	Flame Spread Index -----	Smoke Developed -----
Class I or A:	0 - 25	450 or less
Class II or B:	26 - 75	450 or less
Class III or C:	76 - 200	450 or less

BUILDING CODE CITATION FOR THE CLASSIFICATION SCHEME:

- (1) 2012 edition, NFPA 101 Life Safety Code, para. 10.2.3.4
- (2) 2012 edition, NFPA 5000 Building Construction & Safety Code, para. 10.3.2
- (3) 2012 edition, International Building Code, para. 803.1.1

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM E 84.

Robert I. Brown

 AUTHORIZED SIGNATURE
 THE GOVMARK ORGANIZATION, INC. CT /tm



Received:06/20/2014	Completed:06/26/2014	Letter: J	CT	P.O.#:	Test Report #:	3-02786-0-
---------------------	----------------------	-----------	----	--------	----------------	------------

**Client's
Identification**

Product Identification: Tex Tex / Yuri Material Two Side Coated Vinyl on Polyester Fabric.

Tested For: Doug Johnson

Graniteville Specialty Fabrics
511 Leitner Street
Graniteville, SC 29829

Key Test: ASTM E 84 (BLDG)

1185

Tel: 1-(803)-663-2350

Ext:

Fax: 1-(803)-663-2908

DISCUSSION: Most building codes will accept the ASTM E 84 test when the product is used in a sprinklered area.

If the product is a textile or vinyl wall covering used in a non-sprinklered area, the NFPA 265 room corner fire test applies.

Other wall coverings such as leather, cork, etc. should be tested by NFPA 286.

Certain products are known to give off excessive amounts of heat. A good example is polyurethane foam which is used in cushioned walls.

Such excessive heat producing products should be tested by NFPA 286 even in sprinklered areas.

This discussion is an opinion only. The reader is directed to the actual Building Codes and the Authority Having Jurisdiction.

(Page 3 of 3)