

CAPITANO™

TECHNICAL DATA SHEET

TEST METHOD	RESULT
Fabric Weight ASTM D3776	30 oz/yd.
Width NTC 228	54 inches (137cm)
Bond Strength Adhesion of Vinyl Fim to Fabric Warp ASTM D751	>15 n/in (>3.4 lbf/in)
Bond Strength Adhesion of Vinyl Fim to Fabric Filling ASTM D751	>15 n/in (>3.4 lbf/in)
Resistance of Synthetic Polymeric Material to Fungi ASTM G-21 (No Fungal Growth)	Pass
Antifungal Activity Assement on Textile Materials AATCC 30, Test III (No Growth)	Pass
Colorfastness SAE J 2527 @1500 kj	4+
Crocking AATCC 8 (Wet and Dry)	5
Abrasion Resistance ASTM D4157-07	50,000 double rubs
Tear Strength MD ASTM D 2261	17.6 lbs
Tear Strength CD ASTM D 2261	12.7 lbs
Cold Crack Federal Test Standard (CFFA 6 2007)	-10°F
W-Flex ASTM D2097-03	25,000 cycles
NFPA 260 Class 1	Pass
UFAC Fabric Class 1	Pass
BIFMA Class A	Pass
AB 2998	Pass
California Technical Bulletin #117 TB 117-2013	Pass
Warranty Loss of Strength or color due to normal usage and exposure, and resistance to mildew and atmospheric chemicals	5 Years