

COATED FABRIC PROPERTIES	TEST METHOD	REQUIREMENTS
Color	Visual	Black
Width (trimmed)	ASTM D 751-89, sec. 8	60"
Weight	ASTM D 751-89, sec. 10.2	15.0 – 18.0oz./yd ²
Tongue Tear – Warp	ASTM D 751-89, sec. 22	50.0 lbs. min.
Tongue Tear – Fill	ASTM D 751-89, sec. 22	40.0 lbs. min.
Adhesion – Side 1	Fed. Std. 191A, Method 5970	10.0 lbs/in. min.
Adhesion – Side 2	Fed. Std. 191A, Method 5970	10.0 lbs/in. min.
Dupont Scrubs – Side 1	Trelleborg Method	750 cycles min.
Dupont Scrubs – Side 2	Trelleborg Method	750 cycles min.

Original Date: 04/11

Data presented are averaged results and should not be construed as specification limits.

The information supplied herein is based upon information currently available on the subject. It is offered as a possible helpful guide. Reeves Brothers, Inc., makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. THERE ARE NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY FOR FITNESS OF USE OR OF MERCHANTABILITY, UNLESS EXPRESSLY SET FORTH HEREIN.

TRELLEBORG COATED SYSTEMS US, INC.
 790 Reeves Street
 Spartanburg, SC - 29301
 1-800-635-9350 - fax (864) 595-2211

