

NASSIMI

Nassimi LLC T 212.643.8080
370 Seventh Avenue T 800.521.5208
Suite 1600 F 212.643.2626
New York, NY 10001 W www.nassimi.com

Product Specification Sheet

Pattern: Seaquest

Date: 06/ 22/ 2011

team performance

General Specifications

Weight (linear yard)	32 oz
Width	54 "
Thickness	1 mm
Gauge	0.040
Emboss	Wallaby
Surface Composition	PVC
Substrate Composition	Poly/Rayon
Substrate Weight	3.75 oz

General Treatments

UV Resistance	1,000 Hours	CFFA-2 / ASTM G26-96 Method C
Cold Crack	-10 F	CFFA-6 Federal Standard No. 191A-Method 5874
Mildew Resistant	Pass	CFFA-120 / ASTM G21-96
Anti-Bacterial	N/A	CFFA-300 / AATCC* Test Method 147-1998
Anti-Microbial	N/A	CFFA-300 / AATCC* Test Method 147-1998
Resilience SR	N/A	
Bleach Resistant	N/A	

Physical Strength Properties

Abrasion	175,000+ Cycles		CFFA-1A/ Method ASTM D 4157-92
Adhesion	N/A Warp	N/A Fill	CFFA 3/ ASTM D751-98
Tear Strength	25.8 Warp	27.7 Fill	CFFA-16/ ASTM D5733-95
Tensile Strength & Elongation	89.2 Warp	102.7 Fill	CFFA-17/ ASTM D751-98
Seam Strength	N/A Warp	N/A Fill	CFFA-14/ Method ASTM D751-98
Flex Resistance of Finish	N/A Warp	N/A Fill	CFFA-15/ SAE Method J-855

Flame Retardancy Standards

California Technical Bulletin 117	Pass	NFPA 260	N/A
UFAC Class I	Pass	Boston Fire Code (BFD IX-1)	N/A
BIFMA CS-191-53, Section 3	Pass	IMO A.652(16)8.2	N/A
BIFMA Upholstery, Section 4	Pass	ASTM E84: Class 1 or A Rating	N/A
MVSS 302	Pass		