



STYLE: G16330
Vinyl Coated Polyester
Asphalt Material

TYPICAL PERFORMANCE PROPERTIES

<u>Total Weight</u> ASTM D-751	16 oz. / yd. ²
<u>Grab Tensile</u> ASTM D-751	430 x 335 lbs.
<u>Strip Tensile</u> ASTM D-751 Procedure B	320 x 200 lbs. / in.
<u>Tongue Tear</u> ASTM D-751 8x10 Specimen @ 12 in. / min.	150 x 130 lbs.
<u>Adhesion</u> ASTM D-751 RF Weld	10 lbs. / in.
<u>Puncture Resistance</u> ASTM D-4833	190 lbs.
<u>Hydrostatic Resistance</u> ASTM D-751 Procedure A	680 psi
<u>Low Temperature</u> ASTM D-2136	- 40° F
<u>High Temperature Resistance</u>	180° F Constant 200° F Intermittent
<u>Mildew Resistance</u> ASTM G-21	No Growth

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith.

We make no guarantee of results and no representation that the material is fit for any particular purpose.

There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by Trivantage, LLC.